

1.0 - GENERAL

1.1 Scope

The work under this section consists of all rough carpentry work.

1.2 General

A. Rough carpentry shall generally include all rough framing, furring, grounds, bucks, blocking and such other wood work as required.

B. Carpentry shall also include all temporary bracing, shoring and centering as required for the support or protection of the work.

1.3 Cooperation With Other Trades

The work under this section includes the necessary cutting and patching required for the proper installation of work of other trades. Work which is to be built in by others shall be accurately positioned and properly built in to secure the work of this section. Temporary centering, bracing and shoring shall be provided as required for the support and protection of masonry work during construction.

1.4 Delivery and Storage

Lumber and other materials specified herein shall be delivered, handled and stored in order to prevent damage and absorption of excess moisture. Lumber shall be stored in such a manner as to insure proper ventilation and protection from the weather.

2.0 - PRODUCTS

2.1 Lumber

A. All dimensional lumber used under this section shall be thoroughly dried No. 2 Southern Yellow Pine or No. 2 Douglas Fir of sizes, shapes and lengths required. Moisture content shall not exceed 19% at time of installation.

B. All wood shall be sound, flat, straight, well seasoned, thoroughly dry and free from structural defects. Warped or twisted wood shall not be used.

C. Lumber grades shall conform to the grading rules of the manufacturer's association under whose rules the lumber is produced. All lumber shall be grade-marked.

2.2 Plywood

A. Each panel of softwood plywood shall be identified with the DFPA grade trademark of the American Plywood Association, and shall meet the requirements of Product Standard PS 1-66 for Softwood Plywood Construction and Industrial. All plywood which has any edge or surface permanently exposed to the weather shall be of the exterior type.

B. Plywood sheathing and/or decking shall be DFPA Standard with exterior glue, thickness as shown on the drawings or required for the intended use. Square edge or tongue and groove as approved.

2.3 Wood Treatment

A. Lumber in contact with concrete or masonry, including roof blocking, cants and nailers and/or as indicated, shall be pressure preservative treated in accordance with American Wood Preservers Institute Standard No. LP-2. Creosote, oil or similar materials which bleed shall not be used.

- B. Lumber for blocking and furring, located within interior concealed spaces shall be non-combustible. Treatment shall be equal to "Flame-Proof" by Osmose Wood Preservative; "Non-Con" by Koppers, or approved equal. Lumber shall be UL certification marked.
 - C. Pressure Treated wood associated with roof and roof edge construction which will be in contact with steel or galvanized steel components shall be wrapped or covered with Ice & Water Shield to prevent direct contact between pressure treated wood and steel.
- 2.4 Fastening Devices
Nails, screws, bolts, anchors, washers, clips, shields, power actuated devices and other rough hardware shall be of the sizes and types indicated on the drawings or as required to adequately anchor all members. Anchors for nailing strips and blocking shall have nuts and washers countersunk and bolts cut off flush with the top of the wood nailer. All fasteners in contact with pressured treated wood shall be galvanized.
- 2.5 Temporary Closures
Provide batten doors with locks at all exterior openings. Appropriate protection against weather and life safety shall be maintained throughout the job.
- 2.6 Blocking
Provide solid blocking at all grab bars, millwork cabinets and wall mounted units. Coordinate with Installer and/or Manufacturer.

3.0 - EXECUTION

- 3.1 Installation
- A. All work shall be installed plumb and true, and secured in place with proper fastenings so as to make rigid and firm.
 - B. The work of this section shall be performed in the best practice relating to the trade so as to carry out the intent of the drawings and to properly accommodate the work of all trades.
 - C. Cut ends or faces of all treated wood shall be brushed treated with preservative.
 - D. Wood Studs shall not exceed 16" o.c.. Provide stud framing for walls to receive ceramic tile at 12" o.c..
 - E. Plywood Roof Decking shall be installed with a 1/8" expansion gap between abutting sheets, all sides.
 - F. All Roof Deck fasteners shall be 100% within roof framing. Nails missing or bypassing structural rafter members shall be subject to correction.

END OF SECTION